

**Economic and Social Council**Distr.: General
21 December 2016

Original: English

Economic Commission for Europe**Inland Transport Committee****World Forum for Harmonization of Vehicle Regulations****171st session**

Geneva, 14-17 March 2017

Item 4.8.8 of the provisional agenda

1958 Agreement:**Consideration of draft amendments****to existing Regulations submitted by GRSG****Proposal for the 03 series of amendments to Regulation
No. 118 (Burning behaviour of materials)****Submitted by the Working Party on General Safety Provisions***

The text reproduced below was adopted by the Working Party on General Safety Provisions (GRSG) at its 111th session (ECE/TRANS/WP.29/GRSG/90, para. 40). It is mainly based on ECE/TRANS/WP.29/GRSG/2016/24 as reproduced in Annex III to the report. It is submitted to the World Forum for Harmonization of Vehicle Regulations (WP.29) and to the Administrative Committee AC.1 for consideration at their March 2017 sessions.

* In accordance with the programme of work of the Inland Transport Committee for 2016–2017 (ECE/TRANS/254, para. 159 and ECE/TRANS/2016/28/Add.1, cluster 3.1), the World Forum will develop, harmonize and update Regulations in order to enhance the performance of vehicles. The present document is submitted in conformity with that mandate.

List of contents

Item 5., amend to read:

- "5. Part I: Approval of a vehicle type with regard to the burning behaviour of the components used in the interior compartment, the engine compartment and any separate heating compartment and with regard to the burning behaviour of electric cables and cable sleeves or cable conduits used in the vehicle and/or the capability to repel fuel or lubricant of insulation materials used in the engine compartment and any separate heating compartment."

Annexes, insert a new reference to Annex 10 to read:

- "10 Test to determine the resistance to flame propagation of electrical cables"

Paragraph 1.2. (Scope), amend to read:

- "1.2. Part I - Approval of a vehicle type with regard to the burning behaviour and/or the capability to repel fuel or lubricant of the components used in the interior compartment, the engine compartment and any separate heating compartment and with regard to the burning behaviour of electric cables and cable sleeves or cable conduits used for protecting electric cables in the vehicle."

Insert new paragraphs 2.10. to 2.12., to read:

- "2.10. *"Electrical cable"* means a single-core or multi-core cable, when applicable sheathed, screened and unscreened, two or more cores running side by side and bonded, twisted, or braided together, including cores to form a single assembly enabling the transfer of electrical signals from one device to the other.
- 2.11. *"Cable sleeve"* means any component that enfolds single cables to a multi-core cable or electrical harness.
- 2.12. *"Cable conduit"* means any component that covers electrical cables to guide or route the cables (e.g. tubes, channels, ducts) or fasten electrical cables to the vehicle."

Paragraph 4.2., replace the figure "02" by "03" (2 times).

Paragraphs 5.2.1. and 5.2.2., amend to read:

- "5.2.1. The materials inside and no more than 13 mm beyond the interior compartment, materials of the engine compartment, materials of any separate heating compartment and electric cables, cable sleeves or cable conduits used in the vehicle to be type approved shall meet the requirements of Part II of this Regulation.
- 5.2.2. The materials and/or equipment used in the interior compartment, the engine compartment and any separate heating compartment and/or in devices approved as components, electric cables and cable sleeves or cable conduits used in the vehicle shall be so installed as to minimize the risk of flame development and flame propagation."

Paragraph 6.2.6., amend to read:

- "6.2.6. Any electrical cable exceeding a length of 100 mm used in the vehicle shall undergo the resistance to flame propagation test described in Annex 10 to this Regulation. As an alternative to these requirements, the test procedure described in ISO Standard 6722-1:2011, paragraph 5.22. may be applied.

Test reports and approvals of components obtained according to ISO 6722:2006, paragraph 12. shall remain valid.

The exposure to the test flame shall be finished:

- (1) For single-core cables:
 - (a) When the conductor becomes visible, or
 - (b) After 15 s for cables with conductor sizes less or equal than 2.5 mm², and
 - (c) After 30 s for cables with conductor sizes greater than 2.5 mm²,
 or
- (2) For sheathed, screened and unscreened single- or multi-core cables with a sum of conductor sizes smaller than or equal to 15 mm²:
 - (a) Until a conductor becomes visible or for 30 s, for all cables, whichever comes first,
 or
- (3) For sheathed, screened and unscreened single- or multi-core cables with a sum of conductor sizes greater than 15 mm²:
 - (a) According to (1) or (2), whichever is applicable.

Electrical cables according to (2) may be tested either completely or separately.

Electrical cables according to (3) shall be tested separately.

The result of the test shall be considered satisfactory if, taking into account the worst test result, any combustion flame of insulating material shall extinguish within 70 seconds and a minimum of 50 mm insulation at the top of the test sample shall remain unburned."

Insert a new paragraph 6.2.7., to read:

- "6.2.7. Any cable sleeve or cable conduit exceeding a length of 100 mm shall undergo the test to determine the burning rate of materials as specified in Annex 8. The result of the test shall be considered satisfactory if, taking the worst test results into account, the vertical burning rate is not more than 100 mm/minute or if the flame extinguishes before the destruction of one of the first marker threads occurred."

Paragraphs 6.2.7. to 6.2.7.4. (former), renumber as paragraphs 6.2.8. to 6.2.8.4.

Add new paragraphs 12.11. to 12.14. (Transitional provisions), to read:

- "12.11. As from the official date of entry into force of the 03 series of amendments, no Contracting Parties applying this Regulation shall refuse to grant approval under this Regulation as amended by the 03 series of amendment.
- 12.12. As from 1 September 2019, Contracting Parties applying this Regulation shall grant approvals only if the vehicle type or component type to be approved meet the requirements of this Regulation as amended by the 03 series of amendments.
- 12.13. As from 1 September 2021, Contracting Parties applying this Regulation may refuse first national registration (first entry into service) of a vehicle which does not meet the requirements of this Regulation as amended by the 03 series of amendments.

- 12.14. Even after the date of entry into force of the 03 series of amendments, approvals of the components to the preceding series of amendments to the regulation shall remain valid and Contracting Parties applying the Regulation shall continue to accept them."

Annex 5 (Arrangements of approval marks), replace the figure "02" by "03" (8 times).

Annex 6,

Insert a new paragraph 3.1.3., to read:

- "3.1.3. The size of the sample shall be mentioned in the test report."

Annex 7,

Insert a new paragraph 3.1., to read:

- "3.1. The size and the mass of the sample shall be mentioned in the test report."

Annex 8,

Paragraph 2.1., amend to read:

- "2.1. The specimen holder shall consist of a rectangular frame of 560 mm high and shall have two rigidly connected parallel rods spaced 150 mm apart on which pins shall be fitted for mounting the test specimen which is located in a plane at least 20 mm from the frame. The mounting pins shall be not greater than 2 mm in diameter and at least 40 mm long. The pins shall be located on the parallel rods at locations shown in Figure 1. The frame shall be fitted onto a suitable support to maintain the rods in a vertical orientation during testing (for the purpose of locating the specimen on the pins in a plane away from the frame, spacer stubs 2 mm in diameter may be provided adjacent to the pins).

The specimen holder shown in Figure 1 may be modified in width to allow the fixation of the sample.

To fix the sample in a vertical position, a support may be provided consisting of 0.25 mm diameter heat resistant wires that horizontally span the sample at 25 mm intervals along the complete height of the specimen holder. Alternatively, the sample may be fixed by additional clamps to the specimen holder."

Paragraph 2.3., amend to read:

- "2.3. The test apparatus may be placed in a fume cupboard assembly. The size and shape of the fume cupboard shall be such that the test results are not affected. Before the test, the vertical velocity of the air through the fume cupboard shall be measured 100 mm in front of and behind the final position where the test apparatus will be located. It shall be between 0.10 and 0.30 m/s in order to avoid possible discomfort, by combustion products, to the operator. It is possible to use a fume cupboard with natural ventilation and an appropriate air velocity."

Paragraphs 3.1. and 3.2., amend to read:

- "3.1. Materials according to paragraph 6.2.3. of this Regulation: The samples dimensions are 560 mm x 170 mm.

If the dimensions of a material do not permit taking a sample of the given dimensions the test shall be carried out taking a sample having the dimensions of at least 380 mm in height and at least 3 mm in width.

Cable sleeves and cable conduits: The samples dimensions are: length: 560 mm, but at least 380 mm if the dimensions of a material do not permit taking a sample of the given dimensions; width: actual component dimension.

- 3.2. Materials according to paragraph 6.2.3. of this Regulation: When the thickness of the sample is more than 13 mm, it shall be reduced to 13 mm by a mechanical process applied to the side which does not face the respective compartment (interior, engine or separate heating compartment). If it is impossible, the test shall be carried out in accordance with the Technical Service the initial thickness of the material, which shall be mentioned in the test report. Composite materials (see paragraph 6.1.3.) shall be tested as if they were of uniform construction. In the case of materials made of superimposed layers of different composition which are not composite materials, all the layers of material included within a depth of 13 mm from the surface facing towards the respective compartment shall be tested individually."


Insert a new paragraph 3.3., to read:

"3.3. The size of the sample shall be mentioned in the test report."

Paragraph 3.3. (former), renumber as paragraph 3.4.

Figure 1, amend to read (removing "Burner" at the bottom and replacing "220" by "240"):

"Figure 1
Specimen holder (Dimensions in millimetres)



Insert a new Annex 10, to read:

"Annex 10

Test to determine the resistance to flame propagation of electrical cables

1. Scope
 This annex defines prescriptions to test the resistance to flame propagation of electrical cables used in the vehicle.
2. Sampling and principle
- 2.1. Five samples shall undergo the test
3. Samples

- 3.1. Test samples shall have a length of at least 600 mm of insulation.
- 4. Procedure

Determine the resistance to flame propagation using a Bunsen burner with an appropriate gas, having a combustion tube of 9 mm internal diameter, where the flame temperature at the tip of the inner blue cone shall be $(950 \pm 50)^\circ\text{C}$.

Suspend the test sample in a draught-free chamber and expose the test sample to the tip of the inner cone of the flame, as shown in Figure 1. The upper end of the cable shall point away from the closest wall of the chamber. The sample shall be subject to a stress, e.g. by means of a weight over a pulley, in order to keep it straight at all times. The angle of the cable shall be $45^\circ \pm 1^\circ$ relative to the vertical line. In any case, the shortest distance of any part of the sample shall be 100 mm minimum from any wall of the chamber. Apply the flame with the tip of the inner blue cone touching the insulation (500 ± 5) mm from the upper end of the insulation.

Figure 1
Apparatus for resistance to flame propagation (Dimensions in millimetres)

